Covered Electrodes

CUTTING ROD

For special purpose (Cutting operation)

Description

- Cutting of carbon steels, cast irons, stainless steels and nonferrous alloys, etc.
- Designed for high efficiency in cutting of all kinds of steel.
- · Quiet and stable arc.
- · Excellent usability.
- When the electrodes have absorbed moisture, redry the electrode at 70~80°C for 30 minutes prior to use.

Illustration

· Removal of protrusion





· Removal of down gate, cross gate, etc.





Sizes available and recommended currents (AC or DC -)				
Dia. Length	(mm) (mm)	3.2 350	4.0 400	5.0 400
Amp. (A)	F	150~130	230~180	300~400