

Covered Electrodes

# K-7018G

For low temperature service steel (490MPa)

## Classifications

EN ISO 2560-A:2006	: E 42 5 1Ni B 32 H5	JIS Z 3211	: E4918-G H5
EN ISO 2560-B:2006	: E 49 18-G A H5		
AWS A5.5-06	: E7018-G H4R		

## Description

- Covering is low hydrogen, iron powder type for welding of 1%Ni steel and aluminium-killed steel used at low temperature, LPG tanks, etc.
- Fast, efficient metal transfer in all positions and very low hydrogen contents. (HD  $\leq$  4ml/100g)
- Excellent notch toughness of the deposited weld metal at low temperature.
- Redry the electrode at 300~400°C for 1~2 hours prior to use.

## Welding positions



## Typical chemical composition of all-weld metal (%)

C	Si	Mn	P	S	Ni	Cr	Mo	V
0.04	0.24	0.91	0.016	0.016	1.01	0.05	0.02	0.01

## Typical mechanical properties of all-weld metal

	Y.S (MPa)	T.S (MPa)	EI. (%)	-30°C	-50°C	IV (J)	Remarks
AWS A5.5	min. 390	min. 490	min. 22				
EN ISO 2560-A	min. 420	500~640	min. 20			$\geq 47$	
Example	520	600	34	100	70		AW

\* AW : As-Welded

## Sizes available and recommended currents (AC or DC +)

Dia. Length	(mm) (mm)	2.6	3.2	4.0	5.0
		350	350	400	400
Amp. (A)	F V · OH	60~90 50~80	90~140 80~120	150~190 120~160	180~230 —